



**FORDEX
PTY LTD**

142 Fitzgerald Road
Laverton North
Victoria Australia 3026
Phone 61 3 9369 3455
Fax 61 3 9360 0876

TRADEPAINTS RAPID DRY ENAMEL
Industrial coating – Rapid dry – High gloss.

DESCRIPTION

A quick drying industrial enamel with an excellent gloss, Tradepaints **Rapid Dry Enamels** give a tough, durable finish with outstanding adhesion suitable for interior and exterior applications on suitably prepared metal and timber surfaces.

SURFACE PREPARATION

Remove any rust, scale, dirt, weld slag or old paint by grinding, wire brushing or sanding. Ensure surface to be painted is clean, dry and free from any grease, oil, etc. using metal cleaning and etching fluid. Thoroughly sand existing paint surfaces to remove all surface gloss.

Apply one coat of an appropriate primer where necessary. Tradepaints **Super Etch Primer** for non-ferrous surfaces or Tradepaints **Industrial Primer** for most other metal surfaces.

APPLICATION

Stir thoroughly before and during use with a flat bladed stirrer.

Apply by either conventional or airless spray equipment.

Apply 2 – 3 coats with an even, overlapping pattern, leaving 5 minutes drying time between coats.

THINNING AND CLEAN UP

For conventional spray guns, the product may be reduced up to 15% with Tradepaints Spraying Enamel Thinners.

Wash all equipment with Tradepaints Spraying Enamel Thinners immediately after use.

COVERAGE

Spread rate - 12 to 14 sq. metres per litre per coat.

DRYING

Touch dry: 30 minutes at 20°C

Hard dry: 24 hours at 20°C

Should recoating be necessary, allow 48 hours drying before spraying further coats.

COLOURS

Range of colours available.



CAUTIONS

Flammable liquid – keep away from sources of ignition and naked flames. No smoking.

Harmful by inhalation, contact with skin and if swallowed – avoid contact with the skin and eyes and avoid breathing the vapours.

Provide adequate ventilation in enclosed areas during application and until fully dried.

Do not empty into the drains.

	Pack size: 4 Litre, 1 Litre.				
	COVER	CLEAN UP	DRY TIME	RECOAT	
	12 -14 sq. mt/Lt.	Spraying Enamel Thinners	30 minutes @ 20°C	48 Hours	
Tradepaints is a Trademark of Fordex Pty. Ltd. ACN 075 269 448				Revision a – May 2004	

MSDS Ref: ACT 566.1, 566.2 (Lead Colours)